

TECHNICAL DATA SHEET



Crown Wallplast Skim coat

PRODUCT DESCRIPTION

Type: A white cement-based filler supplied in powder form

Recommended use: Base coat to cover unevenness and pinholes on interior and exterior surfaces

Substrates: Interior and exterior Plasterwork, brick, block, concrete and Timber

Advantages: Excellent workability. Ease of use at site. Interior and Exterior Use. Breathable – can be used even if walls still have some moisture. Cement based hence better compatibility and good adhesion with cement plaster base. Non-flammable.

PRODUCT DATA:

Colour Range: White

Pack Sizes: 20kg bag

Finish: Matt and smooth when sanded with fine abrasive paper.

Thinner & equipment cleaner: Water

Mixing: Mix 2 parts powder and 1-part water by volume. Add water to the powder with mixing until the desired consistency is achieved. Leave to mature for 10 minutes. Remix again for 2 minutes. Product has a short pot-life of 1 hour at 25°C. Mix only enough quantity to be used within the pot-life.

Drying Times: **Surface dry:** 1 hour. **Setting time:** 2 hours. **Dry to sand:** 4 hours.

APPLICATION DATA:

The product can be applied by: Steel trowel or spatula

Spreading Capacity per coat: Depends on film thickness applied, type of texture, surface porosity, imperfections, temperature & wastage during painting.

18 - 20m² per pack @1 – 1.5mm thickness.



TECHNICAL DATA SHEET

Surface preparation & Application:

Surface	Preparation	Application
New masonry or wood surface	Brush out any loose dust, chalk, grease, fungi, algae and old paint flakes. Fill up all major cracks and defects with cement and sand mixture. Thoroughly pre-wet the surface to provide better bonding strength, coverage and ease of application	Apply Wallplast Putty from bottom to upward direction uniformly with the help of a steel trowel to ensure less wastage. Allow to dry for 4-12 hours. After drying of first coat rub the surface very gently with the putty blade to remove loose particles. Apply the 2 nd coat horizontally to even out application marks from the 1 st coat after the 1 st is fully set. Leave to dry overnight to 72hours. The total thickness of the coats should not exceed 2 mm. Sand smooth with P320 grit paper and then apply primer and topcoat

Availability: From Crown Depots in Nairobi, Kisumu, Mombasa, Meru, Nyeri, Eldoret, Arusha, Mwanza, Dar es Salaam, Kigali and through Crown Stockists.

Storage Conditions: Store under cool dry conditions away from direct sunlight, heat and extreme cold.

Disclaimer: The recommendations contained herein are given in good faith and meant to guide the user in accordance with good painting practices. They are gained from our tests and experiences and are believed to be accurate and reliable. No warranty/guarantee is implied by the recommendations contained herein since the conditions of use; application method, substrate and cleanliness of the substrate are beyond Crown Paints Kenya PLC control.

Technology may change with time, necessitating changes to this Technical Data Sheet (TDS).

Crown Paints Kenya PLC reserves the right to amend the TDS without any further notice.

It is the responsibility of the user to ensure that the latest TDS is being used for reference.



For additional health & safety information, please refer to our Material Safety Data Sheet (MSDS)

This Technical Data Sheet supersedes all those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Material Safety Data Sheet (MSDS) for this product. Please visit our website at www.crownpaints.co.ke