

Crown Vesta Skimcoat

PRODUCT DESCRIPTION

Type: A white cement-based filler supplied in powder form

Recommended use: Base coat to cover unevenness and pinholes on interior surfaces

Substrates: Interior Plasterwork, brick, block, concrete and Timber

Advantages: Good workability. Ease of use at site. Breathable – can be used even if walls still have some moisture. Cement based hence better compatibility and good adhesion with cement plaster base. Non-flammable.

PRODUCT DATA:

Colour Range: White

Pack Sizes: 25kg bag

Finish: Matt and smooth when sanded with fine sandpaper.

Thinner & equipment cleaner: Water

APPLICATION DATA:

The product can be applied by: Steel trowel or spatula

Spreading Capacity per coat: Depends on film thickness applied, type of texture, surface porosity, imperfections, temperature & wastage during painting.

12 – 18m² per 25kg bag @1 – 1.5mm thickness for 2 coats.

Surface preparation: Brush out any loose dust, chalk, grease, fungi, algae and old paint flakes. Surfaces with more than 2mm undulations need to be re-plastered. Fill up all major cracks and defects with cement and sand mixture.

Mixing: Mix 2 parts powder and 1-part water by volume. Add the powder to the water with mixing until the desired consistency is achieved. Leave to mature for 10 minutes. Remix again for 2 minutes. Product has a short pot-life of 1 hour at 25°C. Mix only enough quantity to be used within the pot-life.

Application:

- Thoroughly pre-wet the surface to provide better bonding strength, coverage and ease of application. Allow excess water to drip off.
- Apply the first coat of the above mixture to a thickness of 0.5 to 1mm from bottom to upward direction uniformly with the help of a STAINLESS Steel or plastic Trowel or spatula steel trowel to reduce wastage.

TECHNICAL DATA SHEET



If you like it... Crown it!

- Level and smoothen the surface and allow to dry for 4-12 hours.
- After drying of first coat rub the surface very gently with the putty blade to remove loose particles. Apply the 2nd coat 0.5 – 1mm thickness horizontally to even out application marks from the 1st coat and smoothen with a trowel.
- The thickness of each coat must not exceed 1mm and total plaster thickness should not exceed 2mm.
- Leave to dry overnight to 72hours. Sand smooth with P320 or finer sandpaper
- Apply 1 – 2 coats Interior/ Exterior Emulsion Undercoat or 1 coat SB Clear Primer followed by a water based topcoat.

Drying Times: Surface dry: 1 hour. Setting time: 2 hours. Dry to sand: 4 hours.

Availability: From Crown Depots in Nairobi, Kisumu, Mombasa, Meru, Nyeri, Eldoret, Nakuru, Machakos, Arusha, Mwanza, Dar es Salaam, Kigali and through Crown Stockists.

Storage Conditions: Store under cool dry conditions away from humidity, direct sunlight, heat and extreme cold.

Disclaimer: The recommendations contained herein are given in good faith and meant to guide the user in accordance with good painting practices. They are gained from our tests and experiences and are believed to be accurate and reliable. No warranty/guarantee is implied by the recommendations contained herein since the conditions of use; application method, substrate and cleanliness of the substrate are beyond Crown Paints Kenya PLC control. Technology may change with time, necessitating changes to this Technical Data Sheet (TDS). Crown Paints Kenya PLC reserves the right to amend the TDS without any further notice. It is the responsibility of the user to ensure that the latest TDS is being used for reference.



For additional health & safety information, please refer to our Material Safety Data Sheet (MSDS)